



celplast
metallized products



CERAMIS® CPT-036

SILICON OXIDE-COATED POLYESTER FILM

Typical Values

CPT-036 is a SiO_x -coated PET film with a combination of excellent clarity and excellent barrier properties. This grade is suitable for transparent high barrier packaging applications
SiO_x Layer Thickness: ~ 50 nm

Properties	Typical Value		Units	Test Method
Yield	37,400		in ² /lb	
Thickness	0.56 14		Mil µm	
Tensile Strength	33,500 MD 33,500 TD		Psi	ISO 527-1-2
Elongation at break	110 MD 110 TD		%	ISO 527-1-2
Heat Shrinkage	1.3 MD 0.1 TD		%	DIN 40634 150°C, 15 min
Haze	4.0		%	ASTM D1003-92
Static COF	0.70 SiO _x /SiO _x 0.40 PET/PET		-	DIN ISO8295
WVTR	Laminated to 2.8 mil CPP	0.013	g/100in ² /24 hr.	ASTM F1249-90 (73.4° F, 85% RH)
OTR	Laminated to 2.8 mil CPP	0.0032	cc/100in ² /24 hr.	ASTM D-3985 (73.4° F, 50% RH)

This product is in compliance with the regulation FDA 21 CFR 177.1630. When laminated to an approved substrate, the laminate is compliant with the requirements of EU directive 2002/72/EC.

MD = machine direction, TD = transverse direction
All values are with a ± 10% tolerance

The information and opinions herein are believed to be true and accurate and presented without guarantee or responsibility on our part. No recommendation for use of our product is intended as a patent infringement. No warranty of any kind with respect to patents held by others is implied or intended.

February 2016