

CEL-MET[®] BOPP 15 μ m METALLIZED POLYPROPYLENE FILM

Typical Values

Metal One Side, Heat Sealable Other Side

A metallized co-extruded bi-axially oriented polypropylene with the following features:

- _ Wide seal range
- _ Good hot tack
- _ Excellent web flatness
- _ Superior metal adhesion and resistance to “crazing” from extrusion lamination
- _ Outstanding light and moisture barrier

Properties	Typical Value	Units	Test Method
Yield	73,7	m ² /kg	
Thickness	15	μ m	
Tensile Strength	117,2 MD 206,8 TD	N/mm ²	ASTM D882
Tensile Modulus	1723,7 MD 3102,6 TD	N/mm ²	ASTM D882
Elongation	190 MD 70 TD	%	ASTM D882
Optical Density	2,1	Macbeth	CMP OD-1
Light Transmission	< 1,0	%	
Shrinkage (Air oven)	< 5 MD <3 TD	%	5 min, 130 °C
Heat Seal Range	105-150	°C	0.5 s/ 30 psi
WVTR	< 0,5	g/m ² /24 hr	ASTM E-398 (37,8°C, 90% RH)
OTR	< 65	cc/m ² /24 hr	ASTM D-3985 (23°C, 50% RH)

The polypropylene side is in compliance with the regulation FDA 21 CFR 177.1520 (c) (1.1) and (3.1)

The information and opinions herein are believed to be true and accurate and presented without guarantee or responsibility on our part. No recommendation for use of our product is intended as a patent infringement. No warranty of any kind with respect to patents held by others is implied or intended.