



celplast
metallized products



CERAMIS[®] CPT-026

SILICON OXIDE-COATED POLYESTER FILM

Typical Values

CPT-026 is a SiO_x -coated matte PET film with a combination of good barrier properties and matte appearance. This grade is suitable for transparent high barrier packaging applications
SiO_x Layer Thickness: ~ 50 nm

Properties	Typical Value		Units	Test Method
Yield	60		m ² /kg	
Thickness	0.48 12		Mil µm	
Tensile Strength	200 190	MD TD	N/mm ²	ASTM D882
Elongation at break	100 100	MD TD	%	ASTM D882
Heat Shrinkage	2.0 1.0	MD TD	%	DIN 40634 150°C, 30 min
Optical Transparency / Haze	87 / 47		%	ASTM D1003-61
Coefficient of friction (static)	0.70	SiO _x / SiO _x	-	DIN EN ISO 8295
	0.40	PET/PET	-	DIN EN ISO 8295
WVTR	Not specified	Laminated to 75 µm CPP	g/m ² /24 hr.	ASTM F1249-90 (23° C, 85% RH)
OTR	1,5	Laminated to 75 µm CPP	cc/m ² /24 hr.	ASTM D-3985-2005 (23,0° C, 50% RH)

This product is in compliance with the regulation FDA 21 CFR 177.1630. When laminated to an approved substrate, the laminate is compliant with the requirements of EU directive 2002/72/EC.

MD = machine direction, TD = transverse direction
All values are with a ± 10% tolerance

The information and opinions herein are believed to be true and accurate and presented without guarantee or responsibility on our part. No recommendation for use of our product is intended as a patent infringement. No warranty of any kind with respect to patents held by others is implied or intended.

January 2018