

# DURAMET<sup>®</sup> CPP

## METALLIZED CAST POLYPROPYLENE FILM

### Developmental Data Sheet

**Metallized and Top-coated One Side, Heat Sealable Other Side**

High barrier metallized and top-coated cast polypropylene. A highly reflective low slip surface in a differentiated copolymer polypropylene. Provides good machine-ability and side weld seals. Intended for use as combined barrier and sealant layer functional source reduction. *Available 0.80 mil – 2.0 mil*

Properties	Typical Value		Units	Test Method
Yield	36,40		m <sup>2</sup> /kg	
Thickness	1,20 30		Mil µm	
Tensile Strength	47,0 20,0	MD TD	N/mm <sup>2</sup>	ASTM D882
Minimum Heat Seal Strength	5,12		N/25mm	ASTM F 88-85 0.5 sec, 60 psi, 230° F
Ultimate Seal Strength	25,0		N/25mm	ASTM F 88-85 0.5 sec, 60 psi, 252° F
Elongation	400 500	MD TD	%	ASTM D882
Optical Density	2.0		Tobias	CMP OD-1
Light Transmission	< 1.0		%	
Coefficient of Friction	0,18	Kinetic	-	ASTM D1894
WVTR	0,31		g/m <sup>2</sup> /24 hr.	ASTM E-398 (100° F, 90% RH)
OTR	8,0		cc/m <sup>2</sup> /24 hr.	ASTM D-3985 (73.4° F, 50% RH)
Metal Adhesion	3,0		N/25mm	CMP MA-1

The CPP side is in compliance with the regulation FDA 21 CFR 177.1520 (3.1).

The information and opinions herein are believed to be true and accurate and presented without guarantee or responsibility on our part. No recommendation for use of our product is intended as a patent infringement. No warranty of any kind with respect to patents held by others is implied or intended. Celplast does not guarantee the Corona Treatment on metallized CPP films. We suggest applying primer or re-treating in line or consult your ink and adhesive supplier to achieve optimum results.