


ENVIROMET® & DURAMET PLA

Sustainable Solution: Metallized bi-axially oriented PLA film



Sustainable corn-based PLA film.

Compostable – passes ASTM D6400 requirements.



- ◇ High barrier compostable film solution.
- ◇ Printable with 38 natural dyne level.
- ◇ Heat sealable and non-heat sealable grades.
- ◇ Good Seal strength (destruct bond).
- ◇ Excellent flavor, aroma and grease barrier.
- ◇ Responsive technical support.
- ◇ Gauge availability: 80 – 160 ga.
- ◇ BPI Certified

Film Grade	WVTR (g/100in ² /d)	OTR (cc/100in ² /d)	WVTR (g/m ² /day)	OTR (cc/m ² /day)	METAL ADHESION (g/in, MA-1)
DURAMET® PLA	0.06	0.09	0.93	1.395	300
ENVIROMET® PLA	0.2	0.4	3.1	6.2	400