

FOILMET[®] PLUS

METALLIZED POLYESTER FILM

Typical Values

Metal One Side, Corona Treat Other Side

Celplast has developed a metallized PET film which provides guaranteed superior oxygen and water vapor barrier, lot after lot. A surface printable biaxially oriented polyester film exhibiting excellent adhesion and bright foil appearance. Consistently good handling properties, heat stability, slip, and high tensile strength for easy lamination. Featuring superior WVTR, OTR, and light barrier properties.

Properties	Typical Value	Units	Test Method
Yield	59,2	m ² /kg	
Thickness	12	µm	
Tensile Strength	206,8 MD 227,5 TD	N/mm ²	ASTM D882
Elongation	90 MD 70 TD	%	ASTM D882
Heat Shrinkage	1.5 0.2	%	30 min. 70° C.
Optical Density	>2,0	Tobias Densitometer	CMP OD-1
Light Transmission	< 1,0	%	
Coefficient of Friction	0,45 Kinetic 0,55 Static	-	ASTM D1894
WVTR	< 0,31	g/m ² /24 hr	ASTM E-398 (37,8°C, 90% RH)
OTR	< 0,31	cc/m ² /24 hr	ASTM D-3985 (23°C, 50% RH)
Metal Adhesion	6,0	N/25mm	CMP MA-1
Surface Energy on Non-metal side	54	Dyne/cm	ASTM D2578

The polyester side is in compliance with the regulation FDA 21 CFR 177.1630 (f, g, h) and EU Directive 2002/72 and 2011/10.

The information and opinions herein are believed to be true and accurate and presented without guarantee or responsibility on our part. No recommendation for use of our product is intended as a patent infringement. No warranty of any kind with respect to patents held by others is implied or intended.