

SUPERMET® & SUPERMET® HB PET

High Metal Adhesion Polyester

Solve your metal adhesion challenges
with **SUPERMET®** high metal adhesion polyester.

Providing consistent and robust adhesion
no matter what your needs.

SUPERMET is available in varying levels
of barrier and adhesion values to suit
your specific package requirements.

SUPERMET® PET with **metal adhesion**,
certified to a minimum of **600 g/in.**

Typical Barrier Values

Moisture barrier - 0.05 g/100in²/24 hr.

Oxygen barrier - 0.07 cc/100in²/24 hr.

SUPERMET® HB PET superior **metal
adhesion** solution, **certified** to a
minimum of **600 g/in** with excellent
oxygen and moisture barrier values all
in one film.

Typical Barrier Values:

Moisture barrier - 0.03 g/100in²/24 hr.

Oxygen barrier - 0.03 cc/100in²/24 hr.



Applications: food packaging
where improved metal adhesion
and excellent barrier is required.