

DURAMET[®] CPP

METALLIZED CAST POLYPROPYLENE FILM

Developmental Data Sheet

Metallized and Top-coated One Side, Heat Sealable Other Side

High barrier metallized and top-coated cast polypropylene. A highly reflective, low-slip surface in a differentiated copolymer polypropylene. Provides good machineability and side weld seals. Intended for use as a combined barrier and sealant layer for functional source reduction.
Available 1.0 mil – 2.0 mil

Properties	Typical Value		Units	Test Method
Yield	36,40		m ² /kg	
Thickness	1,20 30		mil µm	
Tensile Strength	MD TD	47,0 20,0	N/mm ²	ASTM D882
Minimum Heat Seal Strength	5,12		N/25mm	ASTM F 88-85 0.5 sec, 60 psi, 230° F
Ultimate Seal Strength	25,0		N/25mm	ASTM F 88-85 0.5 sec, 60 psi, 252° F
Elongation	MD TD	400 500	%	ASTM D882
Optical Density	2.0		Tobias	CMP OD-1
Light Transmission	< 1.0		%	
Coefficient of Friction	Kinetic	0,18	-	ASTM D1894
WVTR	0,31		g/m ² /24 hr.	ASTM E-398 (100° F, 90% RH)
OTR	8,0		cc/m ² /24 hr.	ASTM D-3985 (73.4° F, 50% RH)
Metal Adhesion	3,0		N/25mm	CMP MA-1

The CPP side complies with the regulation FDA 21 CFR 177.1520 (3.1).

The information and opinions herein are believed to be true and accurate and presented without guarantee or responsibility on our part. No recommendation for use of our product is intended as a patent infringement. No warranty of any kind with respect to patents held by others is implied or intended. Celplast does not guarantee the Corona Treatment on metallized CPP films. We suggest applying primer or re-treating in line or consult your ink and adhesive supplier to achieve optimum results.