

ULTRAMET™ WR METALLIZED POLYESTER FILM

**Metallized One Side, Corona Treated Other Side
Improved Metal Adhesion and Water Resistance**

A surface or reverse printable biaxially oriented polyester film exhibiting bright foil appearance. For demanding applications that require ultra-high metal to PET adhesion, great water resistance properties, consistently good handling properties, heat stability, slip, and high tensile strength for easy lamination. Excellent WVTR, OTR, and light barrier properties.

Properties	Typical Value	Units	Test Method
Yield	41,600	in ² /lb	
Standard Gauge	0.48	Mil	
Tensile Strength	30,450 MD 30,450 TD	psi	ASTM D882
Elongation	140 MD 110 TD	%	ASTM D882
Optical Density	2.0	Macbeth	CMP OD-1
Light Transmission	1.0	%	
MVTR	0.05	g/100in ² /24 hr.	ASTM E-398 (100° F, 90% RH)
OTR	0.05	cc/100in ² /24 hr.	ASTM D-3985 (73.4° F, 50% RH)
Metal Adhesion	>800* >500**	g/in	CMP MA-1 CMP MA-2
Coefficient of Friction	0.38 0.50	Kinetic Static	ASTM D-1894
Water Immersion	No Degradation***		CMP WI-1

*Certified metal adhesion value

**Value in solvent-based adhesive lamination (PET/Metal/Adhesive/PET)

***Observed after being completely submerged in water for 24 hours at 23°C

The polyester side is in compliance with the regulation FDA 21 CFR 177.1630 (f, g, h)

The metallized side is FDA approved for indirect food contact.

The information and opinions herein are believed to be true and accurate. No recommendation for use of our product is intended as a patent infringement. No warranty of any kind with respect to patents held by others is implied or intended.