

## **CEL-MET<sup>®</sup> CPP 120g**

### **METALLIZED CAST POLYPROPYLENE FILM**

#### **Typical Values**

**Metal One Side, Heat Sealable Other Side**

High barrier metallized cast polypropylene. A highly reflective low slip surface in a differentiated copolymer polypropylene. Provides good machine-ability and side weld seals. Suitable for medical and gel sensitive laminations. *Available 0.80 mil – 2.0 mil*

Properties	Typical Value	Units	Test Method
Yield	25,600	in <sup>2</sup> /lb	
Thickness	1.20 30	Mil μm	
Tensile Strength	6,300 MD 2,800 TD	Psi	ASTM D882
Elongation	400 MD 500 TD	%	ASTM D882
Optical Density	2.0	Macbeth	CMP OD-1
Light Transmission	< 1.0	%	
Coefficient of Friction	0.18 Kinetic	-	ASTM D1894
WVTR	0.04	g/100in <sup>2</sup> /24 hr.	ASTM E-398 (100° F, 90% RH)
OTR	3-5	cc/100in <sup>2</sup> /24 hr.	ASTM D-3985 (73.4° F, 50% RH)
Metal Adhesion	300	g/in	CMP MA-1
Heat Seal Initiation Temperature	230	°F	60psi, 0.5s

The CPP side is in compliance with the regulation FDA 21 CFR 177.1520 (3.1).

The information and opinions herein are believed to be true and accurate and presented without guarantee or responsibility on our part. No recommendation for use of our product is intended as a patent infringement. No warranty of any kind with respect to patents held by others is implied or intended. Celplast does not guarantee the Corona Treatment on metallized CPP films. We suggest applying primer or re-treating in line or consult your ink and adhesive supplier to achieve optimum results.