

## CEL-MET™ BOPP METALLIZED POLYPROPYLENE FILM

### Typical Values

Metal One Side, Heat Sealable Other Side

A metallized co-extruded bi-axially oriented polypropylene with the following features:

- Wide seal range
- Good hot tack
- Excellent web flatness
- Superior metal adhesion and resistance to “crazing” from extrusion lamination
- Outstanding light and moisture barrier

| Properties            | Typical Values   |          | Units                         | Test Method                      |
|-----------------------|------------------|----------|-------------------------------|----------------------------------|
| Thickness             | 15               | 18       | μm                            |                                  |
| Yield                 | 73,7             | 62,6     | m <sup>2</sup> /kg            |                                  |
| Heat Seal Initiation  | 105              |          | °C                            | 0.5 s/ 30 psi                    |
| Tensile Strength      | 117,2<br>206,8   | MD<br>TD | N/mm <sup>2</sup>             | ASTM D882                        |
| Elongation at Break   | 190<br>70        | MD<br>TD | %                             | ASTM D882                        |
| Tensile Modulus       | 1723,7<br>3102,6 | MD<br>TD | N/mm <sup>2</sup>             | ASTM D882                        |
| Dimensional Stability | < 5<br>< 3       | MD<br>TD | %                             | 5 min, 130 ° C                   |
| Optical Density       | 2.0              |          | Tobias Densitometer           | CMP OD-1                         |
| Light Transmission    | < 1.0            |          | %                             |                                  |
| WVTR                  | < 0,5            |          | g/100in <sup>2</sup> /24 hr.  | ASTM D1894                       |
| OTR                   | < 65             |          | cc/100in <sup>2</sup> /24 hr. | ASTM D-3985<br>(73.4° F, 50% RH) |

The polypropylene side is in compliance with the regulation FDA 21 CFR 177.1520 (c) (1.1) and (3.1)

The information and opinions herein are believed to be true and accurate and presented without guarantee or responsibility on our part. No recommendation for use of our product is intended as a patent infringement. No warranty of any kind with respect to patents held by others is implied or intended.