

FOILMET™ BOPP METALLIZED POLYPROPYLENE FILM Typical Values

Metal One Side, Heat Sealable Other Side

A metallized bi-axially oriented polypropylene film exhibiting good metal adhesion and bright foil appearance. It provides consistently good handling properties and heat sealability and features superior WVTR properties.

Properties	Typical Values		Units	Test Method
Thickness	0.60	0.70	Mil	
	15	18	µm	
Yield	51,800	44,000	in ² /lb	
Tensile Strength	MD	17,000	Psi	ASTM D882
	TD	30,000		
Elongation at Break	MD	190	%	ASTM D882
	TD	70		
Tensile Modulus	MD	250,000	Psi	ASTM D882
	TD	450,000		
Dimensional Stability	MD	< 5	%	5 min, 266 ° F
	TD	< 3		
Heat Seal Initiation	220 - 300		°F	½ sec., 30 psi
Optical Density	2.0		Tobias Densitometer	CMP OD-1
Light Transmission	< 1.0		%	
WVTR	< 0.01		g/100in ² /24 hr.	ASTM D1894 (100° F, 90% RH)
OTR	< 3		cc/100in ² /24 hr.	ASTM D-3985 (73.4° F, 50% RH)
Metal Adhesion	250		g/in	CMP MA-1

The polypropylene side is in compliance with the regulation FDA 21 CFR 177.1520 (c) (1.1) and (3.1)

The information and opinions herein are believed to be true and accurate and presented without guarantee or responsibility on our part. No recommendation for use of our product is intended as a patent infringement. No warranty of any kind with respect to patents held by others is implied or intended.