

FOILMET® BOPP

METALLIZED POLYPROPYLENE FILM

Typical Values

Metal One Side, Heat Sealable Other Side

A metallized bi-axially oriented polypropylene film exhibiting good metal adhesion and bright foil appearance. It provides consistently good handling properties and heat sealability and features superior WVTR properties.

Properties	Typical Values		Units	Test Method
Thickness	15	18	µm	
Yield	73,6	62,6	m ² /kg	
Tensile Strength	MD TD	117,2 206,8	N/mm ²	ASTM D882
Secant Modulus	MD TD	1723,7 3102,6	N/mm ²	ASTM D882
Elongation at Break	MD TD	190 70	%	ASTM D882
Dimensional Stability	MD TD	< 5 < 3	%	5 min, 510 °C
Heat Seal Initiation	105-115		°C	0.5 sec., 200 kPa
Optical Density	2.0		Tobias	CMP OD-1
Light Transmission	< 1.0		%	CMP OD-1 ASTM F-1249
WVTR	< 0,16		g/m ² /24 hr	(37,8° C, 90% RH)
OTR	< 46,5		cc/m ² /24 hr	ASTM D-3985 (73.4° F, 50% RH)
Metal Adhesion	2,5		N/25mm	CMP MA-1

The polypropylene side is in compliance with the regulation FDA 21 CFR 177.1520 (c) (1.1) and (3.1)

The information and opinions herein are believed to be true and accurate and presented without guarantee or responsibility on our part. No recommendation for use of our product is intended as a patent infringement. No warranty of any kind with respect to patents held by others is implied or intended.