

CERAMIS®

Clear, high barrier silicone oxide coated film

Celplast is the exclusive North American distributor for the world's most extensive portfolio of clear barrier products:

Base Film	CERAMIS® Grade	Retort-able	Remarks	Typical barrier values in lamination	
				Oxygen cc/100in ² /24 hr.	Water Vapor g/100in ² /24 hr.
Polyester 48 g	CPT-001		MAP lidding, microwaveable pouches and tubes	0.032	0.019
	CPT-002	X		0.032	0.039
	CPT-005	X		0.040	0.045
Oriented Polypropylene 70 g	CPP-004 Heat Sealable		For biscuits, FFS pouches	<0.0065	<0.0065
	CPP-005			<0.0065	<0.0065
Oriented Nylon 60 g	CPA-001		MAP lidding, pouches	0.013	n/a
	CPA-002	X		0.045	
PLA (poly(lactide) acid) 80 g	CPN-003		Renewable corn based film	0.32	0.32



Sales

Jim Lush
 Eastern USA and Canada
 (416) 644-3506
 jim@celplast.com

Veronica Ataya
 Midwest USA and Latin America
 (416) 644-3512
 veronica@celplast.com