



ULTRAMET™ **METALLIZED POLYESTER FILM**

Typical Values **Metal One Side, Corona Treat Other Side**

A surface or reverse printable biaxially oriented polyester film exhibiting bright foil appearance. For demanding applications that require ultra-high metal to PET adhesion. Consistently good handling properties, heat stability, slip, and high tensile strength for easy lamination. Excellent WVTR, OTR, and light barrier properties.

| Properties | Typical Value | Units | Test Method |
|--------------------------------|--------------------------|-------------------------------|---------------------------------|
| Yield | 41,600 | in ² /lb | |
| Standard Gauge | 0.48 12 | mil µm | |
| Tensile Strength | 25,000 MD 30,000 TD | psi | ASTM D882 |
| Tensile Modulus | 530,000 MD 560,000 TD | psi | ASTM D882 |
| Elongation | 120 MD 120 TD | % | ASTM D882 |
| Optical Density | 2.0 | Macbeth | CMP OD-1 |
| Light Transmission | 1.0 | % | |
| Coefficient of Friction | 0.38 0.50 | Kinetic Static | ASTM D-1894 |
| WVTR | 0.05 | g/100in ² /24 hr. | ASTM E398 (100° F, 90% RH) |
| OTR | 0.07 | cc/100in ² /24 hr. | ASTM D3985 (73.4° F, 50% RH) |
| Metal Adhesion | >1000* >500** | g/in | CMP MA-1 CMP MA-2 |

*Certified metal adhesion value tested heat sealing the sample to EAA/Paper/Foil laminate at 250°F/40psi/5s

**Value in solvent-based adhesive lamination (PET/Adhesive/Metal/PET). Dow Adhesive 577/577B. Cured at 35°C/48h.

The polyester side is in compliance with the regulation FDA 21 CFR 177.1630 (f, g, h) and EU Directive 2002/72 and 2011/10. The metallized side is FDA approved for indirect food contact.

The information and opinions herein are believed to be true and accurate. No recommendation for use of our product is intended as a patent infringement. No warranty of any kind with respect to patents held by others is implied or intended.