

## REFLECT-MET®

### Metallized and Top-Coated Building Insulation Film

Top-coated **REFLECT-MET®** PET

Emissivity compares to that of foil at 0.05 - 0.06.

**Corrosion resistance:** coating developed exhibits good temperature resistance and meets ASTM D3310 (7 days at 71 C, 100%RH) corrosion protection requirement on metal surface.

Excellent vapor retarder, passes ASTM E96 perm test after 28 day at 49 C 95%RH (ASTM C1258) at .235 perms.

Bonds well to LLDPE sealant web

Excellent foil-like appearance.



REFLECT-MET used in outdoor wear

**Applications:** include all types of building insulation and other insulating applications.

Sales

**Jim Lush**  
Eastern USA and Canada  
(416) 644-3506  
jim@celplast.com

**Veronica Ataya**  
Midwest USA and Latin America  
(416) 644-3512  
veronica@celplast.com