

ENVIROMET® 80g

HIGH BARRIER METALLIZED POLY(LACTIC) ACID FILM

Typical Values

Metal One Side, No Treat Other Side

A metallized EarthFirst® PLA film, made from a renewable resource: plants. Good handling and excellent barrier properties. Excellent surface brightness and metal adhesion.

Properties	Typical Value	Units	Test Method
Yield	27,600	in ² /lb	
Thickness	0.8 20	Mil µm	
Optical Density	2.0	Macbeth	CMP OD-1
Light Transmission	< 1.0	%	
Coefficient of Friction	0.45 Kinetic 0.55 Static	-	ASTM D1894
WVTR	0.2	g/100in ² /24 hr.	ASTM E-398 (100° F, 90% RH)
OTR	0.4	cc/100in ² /24 hr.	ASTM D-3985 (73.4° F, 50% RH)
Metal Adhesion	400	g/in	CMP MA-1
Ultimate Tensile Strength	8,000 MD 8,000 TD	Psi	ASTM D882
Base Film Compostability	Passed		ASTM D6400

The non-metallized side is FDA approved for direct food contact. Film-to-film heat seals provide film destruct bonds.

The information and opinions herein are believed to be true and accurate and presented without guarantee or responsibility on our part. No recommendation for use of our product is intended as a patent infringement. No warranty of any kind with respect to patents held by others is implied or intended.

This product is made using:

