

REFLECT-MET[®] PET/ White LDPE TOP-COATED METALLIZED POLYESTER FILM, POLY-COATED

Typical Values Coated Metal One Side, White LDPE Other Side

A bi-axially oriented metallized and top-coated polyester facer film exhibiting excellent heat reflection properties, and corrosion resistance, with a bright foil appearance. The metallized PET facer is coated on the opposite side of the metal with 7.5 lbs/ream of white LDPE.

Applications: Reflective and radiant barrier

Properties	Typical Value	Units	Test Method
Yield	24,000	in ² /lb	
Thickness	1.0 25	Mil µm	
Tensile Strength	25,000 30,000	MD TD Psi	ASTM D882
Elongation	90 70	MD TD %	ASTM D882
Optical Density	2.0	Tobias	CMP OD-1
Light Transmission	<1.0	%	
Emissivity	0.06	-	ASTM C1371
Moisture corrosion	Passes	Visual inspection after 7 days accelerated aging	ASTM D3310
Vapor Retarder	0.008 0.235	Perms (not aged) Perms (after 28 days accelerated aging)	Perm - ASTM E96 Aging - ASTM C1258
Metal Adhesion	300	g/in	CMP MA-1
Adhesion of LDPE to Film Substrate	>400 Destruct	g/in	QCP-31

The information and opinions herein are believed to be true and accurate and presented without guarantee or responsibility on our part. No recommendation for use of our product is intended as a patent infringement. No warranty of any kind with respect to patents held by others is implied or intended.