



CAMCLEAR[®] AIOx PET AIOx-coated Polyester Film

Typical Values

AIOx Coated One Side, No Treat Other Side

An AIOx-coated polyester film with great barrier properties and high clarity. Suitable for reverse printing and lamination.

Properties	Typical Values			Units	Test Method
Thickness	0.36 9	0.40 10	0.48 12	Mil µm	
Yield	56,000	50,200	41,600	in ² /lb	
Tensile Strength	MD TD	30,500 32,000	32,000 36,500	Psi	ASTM D882
Elongation	MD TD	120 110	105 85	%	ASTM D882
Visible Light Transmission	87-89			%	
WVTR	0.15			g/100in ² /24 hr.	ASTM E-398 (100° F, 90% RH)
OTR	0.19			cc/100in ² /24 hr.	ASTM D-3985 (73.4° F, 50% RH)
Oxide Adhesion (using 1109 tape)	99%				Camvac Limited Test Method
Surface Energy on AIOx-side	>72			Dyne/cm	ASTM D2578

The polyester side is in compliance with the regulation FDA 21 CFR 177.1630 (f, g, h) and EU Directive 2004/19/EC.

The information and opinions herein are believed to be true and accurate and presented without guarantee or responsibility on our part. No recommendation for use of our product is intended as a patent infringement. No warranty of any kind with respect to patents held by others is implied or intended.