



FOILMET® RR PE SEALANT

HIGH BARRIER METALLIZED POLYETHYLENE FILM

Developmental Data Sheet (Metric)

Metallized one side, Low COF and High Seal strength on other side

- ◆ Excellent oxygen and moisture barrier
- ◆ Low SIT and excellent Heat Seal Strength
- ◆ Recycling ready film for All-PE laminations

Properties		Typical Value			Units	Test Method
Thickness		38	50	89	µm	
Yield		27,6	20,7	11,8	m ² /kg	
Tensile Strength (Break)	MD	26,4		22,0	N/mm ²	ASTM D882
	TD	23,0		2,5		
Secant Modulus (1%)	MD	685		690	N/mm ²	ASTM D882
	TD	755		827		
Elongation	MD	875		600	%	ASTM D882
	TD	900		900		
Elmendorf Tear	MD	100	130	300	g	ASTM D-1922
	TD	40	50	100		
Dart Impact		45	60	60	g	ASTM D-1709 (method A)
Optical Density		2,5				CMP OD-1
Light Transmission		< 1,0			%	
WVTR		1,1	0,8	0,7	g/m ² /24 hr	ASTM F-1249 (37,8°C, 90% RH)
OTR		1,2	0,9	0,6	cc/m ² /24 hr	ASTM D-3985 (23°C, 50% RH)
Metal Adhesion		>10,0			N/25mm	CMP MA-1

This film is in compliance with the regulation FDA 21 CFR 177.1520. Polyethylene surface is approved for direct food contact. Non-objection approval letter is on file from Health Protection Branch of Canadian Food Inspection Agency (CFIA). This film also complies with relevant requirements of the Swiss Chemicals Ordinance SR 813.11 (ChemO) and European Regulation No. 10/2011 for food contact.

The information and opinions herein are believed to be true and accurate and presented without guarantee or responsibility on our part. No recommendation for use of our product is intended as a patent infringement. No warranty of any kind with respect to patents held by others is implied or intended.