

## FOIL-ALOX™ RR BOPE

### HIGH BARRIER TRANSPARENT BOPE

#### Developmental Data Sheet (Metric)

Top-Coated ALOx One Side, Treated Other Side

Properties		Typical Value	Units	Test Method
Thickness		25,0	μm	
Yield		41,0	m <sup>2</sup> /kg	
Tensile Strength	MD	121	N/mm <sup>2</sup>	ASTM D882
	TD	190		
Secant Modulus	MD	1,380	N/mm <sup>2</sup>	ASTM D882
	TD	2,070		
Elongation	MD	140	%	ASTM D882
	TD	25		
Light Transmission		>70	%	CMP OD-1
WVTR		4,0	g/m <sup>2</sup> /24 hr.	ASTM F-1249 (37,8°C, 90% RH)
OTR		1,5	cc/m <sup>2</sup> /24 hr.	ASTM D-3985 (23°C, 50% RH)

This film complies with the regulation FDA 21 CFR 177.1520. The polyethylene surface is approved for direct food contact.

The information and opinions herein are believed to be true and accurate and presented without guarantee or responsibility on our part. No recommendation for use of our product is intended as a patent infringement. No warranty of any kind with respect to patents held by others is implied or intended.