

FOIL-ALOX MDO PE HIGH BARRIER CLEAR ORIENTED POLYETHYLENE FILM

Developmental Data Sheet (Metric)

Top-Coated ALOx One Side, Treated Other Side

Properties		Typical Value	Units	Test Method
Thickness		25,4	µm	
Yield		39,91	m ² /kg	
Tensile Strength (Break)	MD	220	N/mm ²	ASTM D882
	TD	35		
Secant Modulus (1%)	MD	2585	N/mm ²	ASTM D882
	TD	2068		
Elongation	MD	25	%	ASTM D882
	TD	5		
Elmendorf Tear	MD	75	g	ASTM D-1922
	TD	75		
Light Transmission		>70	%	CMP OD-1
WVTR		3,3	g/m ² /24 hr	ASTM F-1249 (37,8°C, 90% RH)
OTR		0,3	cc/m ² /24 hr	ASTM D-3985 (23°C, 50% RH)

This film is in compliance with the regulation FDA 21 CFR 177.1520. Polyethylene surface is approved for direct food contact. Non-objection approval letter is on file from Health Protection Branch of Canadian Food Inspection Agency (CFIA). This film also complies with relevant requirements of the Swiss Chemicals Ordinance SR 813.11(ChemO) and European Regulation No. 10/2011 for food contact.

The information and opinions herein are believed to be true and accurate and presented without guarantee or responsibility on our part. No recommendation for use of our product is intended as a patent infringement. No warranty of any kind with respect to patents held by others is implied or intended.