



celplast
metallized products



CERAMIS® CPN-003

SILICON OXIDE-COATED PLA FILM

Typical Values

CPN-003 is an SiOx -coated Poly (Lactic Acid) film with a combination of excellent clarity, very good barrier properties, and heat seals to itself. This grade is ideally suited for applications that require good barrier, high clarity and full compostability.

Properties	Typical Value	Units	Test Method
Yield	38.9	m ² /kg	
Thickness	0.80 20	Mil μm	
Tensile Strength	99.97 MD 199.95 TD	N/mm ²	ASTM D882
Elongation at break	190 MD 90 TD	%	ASTM D882
Heat Shrinkage	1.3 MD 0.1 TD	%	DIN 40634 150°C, 15 min
Haze	≤3.0	%	ASTM D1003-92
Heat Seal Range	185-284	°F	
Compostability	Passed	-	ASTM D6400
WVTR	20.15	g/m ² /24hr.	ASTM F1249-90 (73.4° F, 85% RH) Unlaminated
WVTR	< 4.96	g/m ² /24 hr.	ASTM F1249-90 (73.4° F, 85% RH) Laminated to 80ga PLA
OTR	20.15	cc/m ² /24 hr.	ASTM D-3985 (73.4° F, 50% RH) Unlaminated
OTR	< 4.96	cc/m ² /24 hr.	ASTM D-3985 (73.4° F, 50% RH) Laminated to 80ga PLA

The PLA side is approved for direct food contact. When laminated to an approved substrate, the laminate is compliant with the requirements of EU directive 2002/72/EC. CERAMIS® PLA-SiOx films are certified by DIN CERTCO and entitled to mark the films with the Compostability Logo, registry no. 7P0116.

The information and opinions herein are believed to be true and accurate and presented without guarantee or responsibility on our part. No recommendation for use of our product is intended as a patent infringement. No warranty of any kind with respect to patents held by others is implied or intended.